



New Pig

Your partner for a clean
and safe workplace.

1-800-HOT-HOGS® (468-4647)

Chemical Compatibility Guide for: PIG® Water-Filled Drain Cover

NOTICE:

The guide on the following page(s) was provided by the supplier. New Pig Corporation assumes no responsibility, obligation, or liability in conjunction with the use or misuse of the information.

**For additional assistance, please contact New Pig Technical Services at
1-800-HOT-HOGS® (468-4647).**

100% Money-Back Guarantee

If you're not happy with a product, for any reason, we'll refund every penny of your purchase price. That means we'll refund all sales taxes, shipping costs, and any other incidentals - without tacking on a restocking fee or any other surprise charges. You get ALL your money back. Period.

One Pork Avenue, Tipton, PA 16684-0304 • 1-800-HOT HOGS® (468-4647) • Fax: 1-800-621-PIGS (7447)
Email: hothogs@newpig.com • Web: newpig.com

© New Pig Corporation. All rights reserved.

EXPOSURE	Rating	EXPOSURE	Rating	EXPOSURE	Rating	Exposure	Rating
AFFF	B	Ethanol	T	JP-4 Jet Fuel	A	Raw Linseed Oil	T
Acetic Acid (5%)	C	Ethyl Acetate	C	JP-5 Jet Fuel	A	SAE-30 Oil	T
Acetic Acid (50%)	C	Ethyl Alcohol	A	Kerosene	A	Salt Water (25%)	T
Ammonium Phosphate	A	Fertilizer Solution	T	Magnesium Chloride	A	Sea Water	A
Ammonium Sulfate	A	#2 Fuel Oil	A	Magnesium Hydroxide	A	Sodium Acetate Solutions	B
Antifreeze (ethylene glycol)	A	#6 Fuel Oil	A	Methanol	A	Sodium Bisulfite Solution	B
Animal Oil	T	Furfural	C	Methyl Alcohol	A	Sodium Hydroxide (60%)	A
Aqua Regia (80%)	B	Gasoline	C	Methyl Ethyl Ketone	C	Sodium Phosphate	A
ASTM Fuel A (100% Iso-octane)	C	Glycerin	A	Mineral Spirits	T	Sulphuric Acid (50%)	A
ASTM Oil #2 (Flash pt. 240° C)	A	Hydraulic Fluid-Petroleum Based	A	Naphtha	B	50% Tanic Acid	A
ASTM Oil #3	B	Hydraulic Fluid-Phosphate Ester Based	C	Nitric Acid (20%)	A	Toluene	C
Benzene	B	Hydrocarbon Type II (40% Aromatic)	C	Nitric Acid (50%)	B	Transformer Oil	T
Calcium Chloride Solutions	A	Hydrochloric Acid (20%)	B	Perchloroethylene	B	Turpentine	B
Calcium Hydroxide	A	Hydrofluoric Acid (100%)	B	Phenol	C	Urea Formaldehyde	T
20% Chlorine Solution	T	Hydrofluoric Acid (50%)	A	Phenol Formaldehyde	X	UAN	A
Clorox	A	Hydrofluosilicic Acid (30%)	A	Phosphoric Acid (50%)	B	Vegetable Oil	A
Conc. Ammonium Hydroxide	A	Isoprophyl Alcohol	T	Phosphoric Acid (100%)	C	Water (120°F)	A
Corn Oil	T	Ivory Soap	A	Phthalate Plasticizer	T	Xylene	C
Crude Oil	10 day	Jet A	A	Potassium Chloride	A	Zinc Chloride	A
Diesel Fuel	10 day			Potassium Sulphate	A		

RATING:

A = Fluid has little or no effect	B = Fluid has minor to moderate effect	C = Fluid has severe effect
T = No data, likely to be acceptable		Qty day = # of days of containment before material degrades and permeates fluid
X = No Data Not likely to be acceptable	NT = Not Tested	